## Order-disorder octahedral tilting transitions in SrSnO<sub>3</sub> perovskite

Elizabeth H. Mountstevens and Simon A. T. Redfern

Department of Earth Sciences, University of Cambridge, Downing Street, Cambridge, CB2 3EQ, United Kingdom

J. Paul Attfield

Centre for Science at Extreme Conditions and School of Chemistry, University of Edinburgh, Mayfield Road, Edinburgh, EH9 3JZ, United Kingdom

(Received 21 December 2004; published 13 June 2005)

High-temperature powder neutron diffraction has been used to characterize two structural phase transitions in the perovskite  $SrSnO_3$ . A continuous orthorhombic *Pnma* to *Imma* symmetry transition occurs at 636 °C, and a first-order transition to a tetragonal *I4/mcm* phase occurs at 800 °C. Such octahedral tilting transitions are very common in perovskite oxides and are generally assumed to be displacive. However, a displacive description of the transitions in  $SrSnO_3$  gives physically unrealistic results, and a considerable dynamic order-disorder component is found. A more realistic order-disorder modeling shows that the population difference between majority and minority tilt states is an appropriate order parameter, and the onset of tilting fluctuations ~300 °C below the *Pnma* to *Imma* transition leads to an unusual divergence of the lattice parameters on warming towards the transition.

DOI: 10.1103/PhysRevB.71.220102

PACS number(s): 61.50.Ks, 61.66.Fn, 64.70.Kb, 81.30.Hd

Structural phase transitions in  $ABO_3$  oxide perovskites are of intrinsic interest as well as being tied to more complex phenomena such as electron-lattice couplings in manganites. There has been a long-running debate about the nature of ferroelectric transitions in perovskites. The ferroelectric phase transitions in BaTiO<sub>3</sub> were originally considered a typical example of a displacive transition. An alternative order-disorder description was suggested by Comes *et al.*<sup>1</sup> based on the observation of diffuse x-ray scattering, although it was subsequentely suggested that this scattering could result from the strong anisotropy of the soft mode.<sup>2</sup> More recent studies of these transitions using Raman spectroscopy<sup>3</sup> and nuclear magnetic resonance<sup>4</sup> reinforce the argument that the transition has a significant order-disorder component. In contrast, phase transitions resulting from the most common type of distortion in perovskites, octahedral tilting, are invariably assumed to be displacive in character.<sup>5,6</sup> In this paper we demonstrate that a typical octahedral tilting transition, in the simple perovskite SrSnO<sub>3</sub>, is principally of orderdisorder character.

 $Sn^{4+}$  is similar in size to  $Ti^{4+}$  and other transition-metal ions but has no off-center, Jahn-Teller, or other single-ion electronic distortions.  $SrSnO_3$  therefore gives useful insights into the evolution of a representative perovskite structure via octahedral tilting.  $SrSnO_3$  is also a good analog to the MgSiO<sub>3</sub> perovskite, believed to be the main constituent of the earth's lower mantle. Detailed investigations on MgSiO<sub>3</sub> are difficult due to the instability of this phase at ambient temperatures and pressures, so  $SrSnO_3$  may provide useful information about structural transformations in MgSiO<sub>3</sub>.

A 10-g polycrystalline SrSnO<sub>3</sub> sample was prepared by sintering a mixture of SrCO<sub>3</sub> and SnO<sub>2</sub> at 1380 °C. Highresolution powder neutron diffraction patterns were collected in the range  $2\theta=4^{\circ}-160^{\circ}$  at a wavelength of  $\lambda=1.593$  Å using the D2B diffractometer at the Institute Laue Langevin (ILL), Grenoble. Diffraction patterns were obtained while heating, every 10 °C between 50 and 800 °C, and every 25 °C up to 875 °C. Rietveld fitting of the data was performed using the GENERAL STRUCTURE ANALYSIS SYSTEM (GSAS) software package,<sup>7</sup> using a linear background function and a pseudo-Voigt diffraction peak shape.

Structural transitions from Pnma to Imma to I4/mcm phases with increasing temperature are found in SrSnO<sub>3</sub> (Fig. 1). The same sequence of transitions has been observed in SrZrO<sub>3</sub> (Ref. 8) and SrRuO<sub>3</sub> (Ref. 9) with temperature, and with increasing x at 300 K in the solid solution  $Sr_xBa_{1-x}SnO_3$  (Ref. 10). The *Imma* to *I*4/*mcm* transition is first order as it involves a discontinuous change from a structure with tilts around a diad axis of the oxygen octahedron to one with the tilts around a tetrad axis.<sup>6</sup> This is consistent with the discontinuity observed in the lattice parameters at the transition temperature of 800 °C (Fig. 1).<sup>11</sup> There is no symmetry discontinuity to the Pnma to Imma transition since it involves loss of the in-phase tilting, so it may be continuous in Landau theory. The lattice parameters vary continuously through the transition, but their divergence on heating towards the transition is very unusual.

Thermal variations of the octahedral tilt angle, the mean Sn-O distance, and the oxygen temperature factors were de-



FIG. 1. Thermal variation of the lattice parameters of  $SrSnO_3$ .

TABLE I. Atomic positions (x, y, z) for the conventional *Imma* and *Pnma* superstructure models, and the disordered model used to fit both phases.  $\pm$  displacements are for the majority (upper) and minority (lower) tilt states.

	Imma	Pnma	Disordered
Sr	(0, 0.25, z)	$(\delta_{\rm xSr}, 0.25, z)$	$(\pm \delta_{\rm xSr}, 0.25, z)$
Sn	(0, 0, 0.5)	(0, 0, 0.5)	(0, 0, 0.5)
01	(0.5, 0.25, z)	$(0.5 - \delta_{\rm xO1}, 0.25, z)$	$(0.5 \pm \delta_{x01}, 0.25, z)$
O2	(0.25, y, 0.75)	$(0.25 + \delta_{xO2}, y, 0.75 - \delta_{zO2})$	$(0.25 \pm \delta_{xO2}, y, 0.75 \mp \delta_{zO2})$

rived by refinement of the atomic parameters in the conventional models (see Tables I and II) for the three phases. The tilt angle is a measure of the order parameter for a displacive transition involving loss of an octahedral tilt. The tilt angles were calculated from the oxygen atomic positions by the method of Kennedy et al.,<sup>12</sup> as implemented in a previous study,<sup>10</sup> and the results are shown in Fig. 2. The variation of the in-phase tilt angle with temperature is described well by a critical equation:  $\phi_{+} = \phi_{+}(0)(1 - T/T_{c})^{\beta}$  and the fitted parameters are  $\phi_+(0) = 7.43(2)^\circ$ ,  $T_c = 908.6(6) \text{ K}(=636 \circ \text{C})$ ,  $\beta$ =0.187(2) for data fitted between 50 and 630 °C. The value of  $\beta$  is lower than expected for a second-order ( $\beta$ =0.50) or a tricritical ( $\beta$ =0.25) displacive phase transition, indicating a first-order or a dynamic order-disorder transition. The latter is particularly likely since similar low values for the critical exponent are found for well-characterized dynamic orderdisorder transitions, e.g., that in KH<sub>2</sub>PO<sub>4</sub> (KDP) for which  $\beta$ =0.168 (Refs. 13 and 14) and CaTiSiO<sub>3</sub> (titanite) where  $\beta = 0.15$  (Ref. 15).

Figure 3 shows the thermal variation of the average Sn-O bond distance given by the standard (displacive) refinement model. The average distance remains approximately constant within the range of each superstructure but shows an unphysical contraction at the transitions to higher-temperature phases. This apparent shortening of the Sn-O distance is an artefact of averaging over disordered tilts (and hence, disordered oxygen positions) in the mean crystallographic structure. Uncorrelated static disorder is not possible in the perovskite framework, as it leads to structural singularities across domain walls. However, short-range correlation can be accommodated in dynamically disordered perovskites through disordered local rigid unit modes, and so our obser-

TABLE II. Atomic positions for the I4/mcm phase in a conventional (displacive) description and the two-tilt state disordered model.

	I4/mcm	Disordered
Sr	(0, 0.5, 0.25)	(0.75, 0.25, 0.75)
		(0.75, 0.25, 0.25)
		$(0.25, 0.25, 0.25 \pm \delta_{xSr})$
Sn	(0, 0, 0)	(0, 0, 0)
01	(0, 0, 0.25)	$(0.5 + \delta_{xO1}, 0.5 + \delta_{xO1}, 0.25)$
O2	(0.25+x, 0.75+x, 0.75)	$(0.25, y, \pm \delta_{zO2})$
		$(0.25, 0.5+y, 0.5\pm\delta_{zO3})$

vations of  $\langle \text{Si-O} \rangle$  behavior point towards the transitions being order-disorder type (similar in character to disordered ferroelectrics, or as is observed in the high-temperature phase of SiO<sub>2</sub> cristobalite<sup>16,17</sup>). The apparent shortening arises when there is significant disordered bending of the Sn-O-Sn bridges around a crystallographic mean in which the Sn-O-Sn angle is near or equal to 180°.

If we do not incorporate such disorder of oxygen into our refinements, the oxygen atomic temperature factors increase steadily across the temperature range of the *Pnma* phase but show a sudden increase at the transition to Imma (Fig. 4). This suggests that the distribution of oxygen positions broadens rapidly on heating through  $T_{c}$ . A similar thermal variation is observed for linewidths in the Raman spectrum of  $BaTiO_3$  (Ref. 3) and is indicative of order-disorder character for the phase transition. Furthermore, this suggests that the spatial distribution of oxygen about the midpoint of Sn-Sn vectors (and associated apparent  $\langle Si-O \rangle$  bond shortening) is not simply due to an increase in the librational amplitude of oxygen perpendicular to the Sn-O bond, as this would increase close to  $T_c$  both on cooling and heating, with critical softening approaching  $T_c$  from above or below. Such a displacive transition with a large anion libration has been reported for the perovskite  $NaMgF_3$  (Ref. 18).

To model the structures more realistically, and thereby the dynamic order-disorder characteristics of the transitions in  $SrSnO_3$ , the structure refinements were repeated with site disorder specifically included. To model the *Pnma* to *Imma* transition, the two superstructures were described by a single model (Table I) containing two sets of atomic positions that



FIG. 2. Thermal variation of in-phase tilt angles  $\phi_+$  and out-ofphase tilt angles  $\phi_-$  in a displacive description. The fitted line is given by the critical equation  $\phi_+ = \phi_+(0)(1-T/T_c)^{\beta}$ .



FIG. 3. Variation of the average Sn-O bond length with temperature in the displacive description of SrSnO<sub>3</sub>.

correspond to the two possible directions of the in-phase tilting distortion. In the *Imma* regime, the populations of the two sets of atomic positions were constrained to be equal (1-p=p=0.5) and the displacement coordinates  $\delta_x$ ,  $\delta_z$ , were refined in addition to the other variable positions. In the *Pnma* region, the same coordinates were refined, but the populations of two sets were varied in the ratio 1-p:p.

The high-temperature I4/mcm phase also shows evidence of oxygen disorder; for example, the low average Sn-O bond distance seen in Fig. 3. *Imma* is not a subgroup of I4/mcm so the disorder present in I4/mcm is not obtained by averaging over that in *Imma*. The approach we have taken is to model the dynamic disorder of the in-phase tilting in I4/mcm on that of  $P4_2/nmc$ , a subgroup of I4/mcm (see Table II).

The variation in average Sn-O bond length determined from the refinements of the above disordered models is shown in Fig. 5. The continuous thermal expansion through the *Pnma* to *Imma* transition demonstrates that this approach is physically realistic; a small (but expansive) discontinuity is observed at the first-order *Imma* to *I4/mcm* transition. Figure 6 shows the thermal variation of the tilt angles through the *Pnma* to *Imma* transition, from refinement of the single disordered model for the two space groups. Both the inphase and out-of-phase tilting angles change by only  $\sim 3^{\circ}$ over the entire temperature interval. The in-phase tilting shows a small critical variation below the *Imma* to *Pnma* 



FIG. 5. Variation of the average Sn-O bond length when modeled with an order-disorder model.

transition, but the magnitude of the increase in  $\phi_+$  is only 1.7° compared to 6.9° in the displacive description (Fig. 2). The ratio of these values, 25%, can be used as a measure of the displacive character of the transition, hence the *Pnma* to *Imma* transition in SrSnO<sub>3</sub> is predominantly (75%) order-disorder.

The order parameter for the transition in this orderdisorder description is the population difference between the two tilted states,  $\eta_{\pm}=1-2p$ . Fitting to a generic critical equation of the type  $\eta_+ \propto (1 - T/T_c)^{\beta}$  gives  $T_c = 903.9(5)$  K. and  $\beta$ =0.160(5) for data fitted between 50 and 630 °C (Fig. 7). The fitted parameters are similar to those derived from fitting the tilt angles in Fig. 2, indicating that tilt angle in a displacive model and occupancy in the order-disorder approach are both measures of the order parameter, and  $\beta = 0.16$  is again consistent with an order-disorder transition.<sup>13,14</sup> However, the quality of this fit is less good since the ordering saturates to unity relatively quickly on cooling from  $T_c$ . We have, therefore, also applied a modified Bragg-Williams model to the  $\eta_+$  data using the method of Hayward *et al.*<sup>19</sup> Fitting the equation  $T = a \eta + b \eta^3 / R(\ln(1+\eta) - \ln(1-\eta))$  to the data we obtain a=15.0(6) kJ mol<sup>-1</sup> and b=4.8(9) kJ mol<sup>-1</sup>, with  $T_{\rm c}$ =903.9 K. This modified Bragg-Williams fit, shown by



FIG. 4. Thermal variation of the isotropic temperature factor of O2.



FIG. 6. Variation of the in-phase tilt angles  $\phi_+$  and out-of-phase tilt angles  $\phi_-$  in the order-disorder description of the *Pnma* to *Imma* transition.

the dashed line in Fig. 7, provides a better description than the generic critical equation, as it takes account of the configurational entropy expected for order-disorder behavior.

The order-disorder description of the Pnma to Imma transition gives insight into the unusual lattice parameter variation (Fig. 1). The region of divergence of the Pnma phase lattice parameters on warming above ~350 °C corresponds to the onset of disorder in the *Pnma* phase (Fig. 7). This results in an *increase* in the apparent orthorhombic spontaneous strain on heating towards the transition to Imma. in contrast to the reduction in strain expected on approaching a displacive transition. Similar divergence was observed in a study of SrZrO<sub>3</sub> (Ref. 6) although the origins were not explored. This divergence of lattice parameters approaching a phase transition has implications for the interpretation of cell parameter data as indicators of proximity to a phase transition. For example, the divergence of lattice parameters in Pnma MgSiO<sub>3</sub> with increasing pressure has been cited as evidence that there is no structural transformation of this phase in the mantle.<sup>20</sup> However, we find that diverging cell parameters in the analog Pnma SrSnO<sub>3</sub> phase signify the approaching transition.

These results also have implications for the interpretation of electronic properties of perovskites. Differences in property (e.g., metal-insulator transitions) resulting from small changes in temperature, pressure, or chemical composition are often rationalized from changes in bandwidth, proportional to  $\cos \phi$ , where  $\phi$  is an averaged tilt angle. In SrSnO<sub>3</sub>, the tilt angles change little over a wide temperature range (Fig. 6), and the large change in apparent tilt angle at the phase transition from a displacive description (Fig. 2) is an artefact of averaging over the changing population difference between majority and minority tilt states.

In conclusion, we have shown that a displacive description of the octahedral tilting transitions in the simple, representative, perovskite  $SrSnO_3$  is misleading, as it neglects a major dynamic order-disorder contribution (76% for the



FIG. 7. Thermal variation of the population difference order parameter,  $\eta_+$  in the order-disorder modeling of the *Pnma* to *Imma* transition. The solid line is a fit of the type  $\eta_+ \propto (1 - T/T_c)^{\beta}$  and the dashed line is the modified Bragg-Williams fit.

*Pnma* to *Imma* transition). Modeling the continuous *Pnma* to *Imma* transition with an order-disorder model leads to a physically realistic thermal variation of the mean Sn-O distance, and demonstrates that an unusual divergence of cell parameters on heating towards the transition is linked to the onset of tilting fluctuations in the low-temperature phase. While order-disorder descriptions have been applied extensively to ferroelectric perovskites, this study demonstrates that such phenomena can also be significant at the more general, tilting distortions of perovskites. Structure refinements and derived results such as electronic-band structures for other perovskites may require consideration of disordered tilting to provide more realistic descriptions of their properties.

We thank Dr. A. Hewat and Dr. E. Suard (ILL) for help in collecting the neutron powder patterns and EPSRC for financial support for E.H.M through Grant No. GR/R88601.

- <sup>1</sup>R. Comes, M. Lambert, and A. Guinier, Solid State Commun. **6**, 715 (1968).
- <sup>2</sup>J. Harada, J. D. Axe, and G. Shirane, Phys. Rev. B **4** 155 (1971).
- <sup>3</sup>N. Baskaram, A. Ghule, C. Bhongale, R. Muragan, and H. Chang, J. Appl. Phys. **91**, 10038 (2002).
- <sup>4</sup>B. Zalar, V. V. Laguta, and R. Blinc, Phys. Rev. Lett. **90**, 037601 (2003).
- <sup>5</sup>P. M. Woodward, Acta Crystallogr., Sect. B: Struct. Sci. 53, 32 (1997).
- <sup>6</sup>C. J. Howard and H. T. Stokes, Acta Crystallogr., Sect. B: Struct. Sci. 54, 782 (1998).
- <sup>7</sup>R. von Dreele and A. C. Larson, GSAS General Structure Analysis System, Los Alamos National Laboratory Report No. LAUR 86-748, 1986 (unpublished).
- <sup>8</sup>C. J. Howard, K. S. Knight, B. J. Kennedy, and E. H. Kisi, J. Phys.: Condens. Matter **12**, L677 (2000).
- <sup>9</sup>B. J. Kennedy, B. A. Hunter, and J. R. Hester, Phys. Rev. B 65, 224103 (2002).
- <sup>10</sup>E. H. Mountstevens, J. P. Attfield, and S. A. T. Redfern, J. Phys.: Condens. Matter **15**, 8315 (2003).

- <sup>11</sup>The same phase transitions have been reported in another recent study of SrSnO<sub>3</sub>[M. Glerup, K. S. Knight, and F. W. Poulsen, Mater. Res. Bull. **40**, 507 (2005)]. In addition, the tetragonal *I4/mcm* to cubic *Pm*-3*m* transition was observed at 1022 °C.
- <sup>12</sup>B. J. Kennedy, C. J. Howard, and B. C. Chakoumakos, J. Phys.: Condens. Matter **11**, 1479 (1999).
- <sup>13</sup>J. W. Benepe and W. Reese, Phys. Rev. B **3**, 3032 (1971).
- <sup>14</sup>R. Kind, P. M. Cereghetti, C. A. Jeitziner, B. Zalar, J. Dolinsek, and R. Blinc, Phys. Rev. Lett. 88, 195501 (2002).
- <sup>15</sup>J. Chrosch, U. Bismayer, and E. K. H. Salje, Am. Mineral. 82, 677 (1997).
- <sup>16</sup>R. Blinc, Ferroelectrics **301**, 3 (2004).
- <sup>17</sup>M. G. Tucker, M. P. Squires, M. T. Dove, and D. A. Keen, J. Phys.: Condens. Matter **13**, 403 (2001).
- <sup>18</sup>J. N. Street, I. G. Wood, K. S. Knight, and G. D. Price, J. Phys.: Condens. Matter **9**, L647 (1997).
- <sup>19</sup>S. A. Hayward, J. del Cerro, and E. K. H. Salje, Am. Mineral. 85, 557 (2000).
- <sup>20</sup>H. K. Mao, R. J. Hemley, Y. Fei, J. F. Shu, L. C. Chen, A. P. Jephcoat, and Y. Wu, J. Geophys. Res. **96**, 8069 (1991).